

BEST CLOTH TAPE NO. 756

15 April 2019

PRERARED BY QES Center

No. NJ-19043

We have investigated the properties of BEST CLOTH TAPE NO. 756 as requested and obtained the following results.

1. Sample

BEST CLOTH TAPE NO. 756

2. Testing items and method

- 1 Thickness . . . To be measured with dial gauge
- 2 Adhesive strength . . . To be measured with tensile tester
Substrate: SUS board. Tensile speed: 300mm/min
- 3 Holding strength . . . Apply 9.81N load to the bonding area (25mmx25mm)
(stainless steel plate) at 40°C, and determine the deviation distance after 30 minutes.
- 4 Unwinding force . . . To be measured with unwinding tester
Unwinding speed: 30m/min
- 5 Tensile strength . . . To be measured with tensile tester
Tensile speed: 300mm/min
- 6 Elongation . . . To be measured with tensile tester
Tensile speed: 300mm/min

3. Properties

Table-1

Testing item		NO. 756
Thickness	(mm)	0.23
Adhesive strength	(N/25mm)	24.20
Holding strength	(mm)	0.1
Unwinding force	(N/25mm)	2.8
Tensile strength	(N/25mm)	186
Elongation	(%)	12

The data is measurement data and is not a warranty data.

Hiroataka Sato

H. Sato
QES Center.

NITTO DENKO CS SYSTEM CORPORATION
TOYOHASHI PLANT.

Notes: This data represents examples of measured values, and not guaranteed values. They do not guarantee compatibility with the applications of your company. Please confirm compatibility with your application prior to use. We retain all rights, including copyrights, for the contents of these documents. Copying, reprinting and use for purposes other than originally intended are strictly prohibited without our prior expressed permission.

Nitto Denko CS System Corporation